

TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371

APV31519

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR

09/936044

INTERNATIONAL APPLICATION NO.
PCT/EP00/02211INTERNATIONAL FILING DATE
March 9, 2000PRIORITY DATE CLAIMED
March 10, 1999

TITLE OF INVENTION

PROCESS FOR PRODUCING A PLASTIC WEB FOR COATING A METAL SUBSTRATE, LAMINATE
COMPRISING THIS PLASTIC WEB, AND PRODUCT OR COMPONENT PRODUCED THEREWITH

APPLICANT(S) FOR DO/EO/US

Petrus Cornelis Jozef BEENTJES Willem Jan VAN VEENEN
Huibert Willem DEN HARTOG

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☐ This is an express request to begin national examination procedures (35 U.S.C. 371(f)). The submission must include items (5), (6), (9) and (24) indicated below.
4. ☐ The US has been elected by the expiration of 19 months from the priority date (Article 31).
5. ☒ A copy of the International Application as filed (35 U.S.C. 371 (c) (2))
 - a. ☒ is attached hereto (required only if not communicated by the International Bureau).
 - b. ☒ has been communicated by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☐ An English language translation of the International Application as filed (35 U.S.C. 371(c)(2)).
 - a. ☐ is attached hereto.
 - b. ☐ has been previously submitted under 35 U.S.C. 154(d)(4).
7. ☒ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371 (c)(3))
 - a. ☐ are attached hereto (required only if not communicated by the International Bureau).
 - b. ☐ have been communicated by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☒ have not been made and will not be made.
8. ☐ An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
9. ☐ An oath or declaration of the inventor(s) (35 U.S.C. 371 (c)(4)).
10. ☐ An English language translation of the annexes of the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371 (c)(5)).
11. ☒ A copy of the International Preliminary Examination Report (PCT/IPEA/409).
12. ☒ A copy of the International Search Report (PCT/ISA/210).

Items 13 to 20 below concern document(s) or information included:

13. ☒ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
14. ☐ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
15. ☒ A **FIRST** preliminary amendment.
16. ☐ A **SECOND** or **SUBSEQUENT** preliminary amendment.
17. ☐ A substitute specification.
18. ☐ A change of power of attorney and/or address letter.
19. ☐ A computer-readable form of the sequence listing in accordance with PCT Rule 13ter.2 and 35 U.S.C. 1.821 - 1.825.
20. ☐ A second copy of the published international application under 35 U.S.C. 154(d)(4).
21. ☐ A second copy of the English language translation of the international application under 35 U.S.C. 154(d)(4).
22. ☐ Certificate of Mailing by Express Mail
23. ☒ Other items or information:

Notice of Claim for Priority

Copy of cover sheet of published PCT application WO 00/53665

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR

INTERNATIONAL APPLICATION NO.

ATTORNEY'S DOCKET NUMBER

PCT/EP00/02211

APV31519

24. The following fees are submitted:.

CALCULATIONS PTO USE ONLY

BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)) :

- ☐ Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO \$1000.00
- ☒ International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO \$860.00
- ☐ International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO \$710.00
- ☐ International preliminary examination fee (37 CFR 1.482) paid to USPTO but all claims did not satisfy provisions of PCT Article 33(1)-(4) \$690.00
- ☐ International preliminary examination fee (37 CFR 1.482) paid to USPTO and all claims satisfied provisions of PCT Article 33(1)-(4) \$100.00

ENTER APPROPRIATE BASIC FEE AMOUNT =

\$860.00

Surcharge of \$130.00 for furnishing the oath or declaration later than ☐ 20 ☐ 30 months from the earliest claimed priority date (37 CFR 1.492 (e)).

\$0.00

CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE
Total claims	36 - 20 =	16	x \$18.00
Independent claims	1 - 3 =	0	x \$80.00

\$288.00

\$0.00

\$0.00

Multiple Dependent Claims (check if applicable).

TOTAL OF ABOVE CALCULATIONS =

\$1,148.00

☐ Applicant claims small entity status. (See 37 CFR 1.27). The fees indicated above are reduced by 1/2.

\$0.00

SUBTOTAL =

\$1,148.00

Processing fee of \$130.00 for furnishing the English translation later than ☐ 20 ☐ 30 months from the earliest claimed priority date (37 CFR 1.492 (f)).

\$0.00

TOTAL NATIONAL FEE =

\$1,148.00

Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31) (check if applicable).

\$0.00

TOTAL FEES ENCLOSED =

\$1,148.00

Amount to be:

refunded

\$

charged

\$

- a. ☒ A check in the amount of 1148.00 to cover the above fees is enclosed.
- b. ☐ Please charge my Deposit Account No. _____ in the amount of _____ to cover the above fees. A duplicate copy of this sheet is enclosed.
- c. ☒ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. 19-4375. A duplicate copy of this sheet is enclosed.
- d. ☐ Fees are to be charged to a credit card. **WARNING:** Information on this form may become public. **Credit card information should not be included on this form.** Provide credit card information and authorization on PTO-2038.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.

SEND ALL CORRESPONDENCE TO:

Anthony P. Venturino
Reg. No. 31,674

STEVENS, DAVIS, MILLER & MOSHER, LLP
1615 L Street NW, Suite 850
Washington, DC 20036

Tel.: 202-785-0100 Fax.: 202-408-5200

SIGNATURE

NAME

31,674

REGISTRATION NUMBER

DATE



09/936044

JC12 Rec'd PCT/PTO 07 SEP 2001

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re the Application

Petrus BEENTJES et al

Serial No: (National Phase of PCT/EP00/02211)

Filed: September 7, 2001

For: PROCESS FOR PRODUCING A PLASTIC WEB FOR COATING A METAL
SUBSTRATE, LAMINATE COMPRISING THIS PLASTIC WEB, AND PRODUCT OR
COMPONENT PRODUCED THEREWITH

PRELIMINARY AMENDMENT

Honorable Commissioner of
Patents and Trademarks
Washington, D.C. 20231

Sir:

Prior to the calculation of the filing fee, please amend the above-identified
application by further amending the claims on the Annexes to the International Preliminary
Examination Report as follows:

IN THE CLAIMS

1. (Amended) Process comprising producing a plastic web for coating a metal
substrate, in which the plastic is polyester, wherein the plastic web is produced by extruding
a mixture of crystallisable polyester and non-crystallisable polyester.

2. (Amended) Process according to Claim 1, wherein the polyesters used are
copolyesters.

3. (Amended) Process according to Claim 2, wherein copolyesters based on
terephthalic acid are used.

4. (Amended) Process according to Claim 3, wherein polyesters, which are formed

09/936044

on the basis of PET, are used.

5. (Amended) Process according to Claim 1, wherein the non-crystallisable polyester used is a copolyester containing CHDM (1,4-cyclohexanedimethanol).

6. (Amended) Process according to Claim 5, wherein the CHDM-modified copolyester is obtained by reacting a mixture of terephthalic acid, ethylene glycol (ethanediol) and CHDM.

7. (Amended) Process according to Claim 1, wherein the non-crystallisable polyester used is a PET/PEN copolymer, which is obtained by reacting a mixture of terephthalic acid, naphthalenedicarboxylic acid and ethylene glycol (ethanediol).

8. (Amended) Process according to Claim 1, wherein the mixture has a non-crystallisable weight fraction, which is greater than 6%.

9. (Amended) Process according to Claim 8, wherein the mixture has a non-crystallisable weight fraction, which is less than 90%.

10. (Amended) Process according to Claim 8, wherein the mixture used has a non-crystallisable weight fraction which is 25% or greater.

11. (Amended) Process according to Claim 8, wherein the mixture has a non-crystallisable weight fraction which is 33% or greater.

12. (Amended) Process according to Claim 8, wherein the mixture has a non-crystallisable weight fraction which is 50% or greater.

13. (Amended) Process according to Claim 8, wherein the mixture has a non-

crystallisable weight fraction which is 66% or greater.

14. (Amended) Process according to Claim 8, wherein the mixture has a non-crystallisable weight fraction which is 75% or greater.

15. (Amended) Laminate comprising a metal substrate and a plastic layer, wherein the plastic layer comprises an adhesive layer, the adhesive layer substantially comprising a plastic web produced according to the process described in Claim 1.

16. (Amended) Laminate comprising a metal substrate and a plastic layer, wherein the plastic layer comprises a top layer, the top layer substantially comprising a plastic web produced according to the process described in Claim 1.

17. (Amended) Laminate according to Claim 15, wherein there is an intermediate layer between the adhesive layer and the top layer, the intermediate layer substantially comprising a plastic web, which is produced by extruding a polyester.

18. (Amended) Laminate according to Claim 17, wherein the intermediate layer is produced according to the process described in Claim 1.

19. (Amended) Laminate according to Claim 18, wherein the intermediate layer is produced from a mixture with a non-crystallisable weight fraction which is 10% or greater.

20. (Amended) Laminate according to Claim 19, wherein the intermediate layer is produced from a mixture with a non-crystallisable fraction which is 33% or greater.

21. (Amended) Screw cap produced from a laminate according to Claim 15.

22. (Amended) Crown cork produced from a laminate according to Claim 15.
23. (Amended) Easy open end produced from a laminate according to Claim 15.
24. (Amended) Component produced from a laminate according to Claim 16, in which a PVC-containing compound is applied to the top layer of the plastic layer of the laminate.
25. Component according to Claim 24, in which the non-crystallisable weight fraction in the top layer is 25% or greater.
26. Component according to Claim 24, in which the weight fraction is 35% or greater.
27. (Amended) Component according to Claim 26, in which the weight fraction is 50% or greater.
28. (Amended) Component according to Claim 27, in which the weight fraction is 66% or greater.

Please add the following new claims.

30. Laminate according to Claim 16, wherein there is an intermediate layer between the adhesive layer and the top layer, the intermediate layer substantially comprising a plastic web, which is produced by extruding a polyester.
31. Laminate according to Claim 30, wherein the intermediate layer is produced according to the process described in Claim 1.

32. Laminate according to Claim 31, wherein the intermediate layer is produced from a mixture with a non-crystallisable weight fraction which is 10% or greater.

33. Screw cap produced from a laminate according to Claim 16.

34. Crown cork produced from a laminate according to Claim 16.

35. Easy open end produced from a laminate according to Claim 16.

36. Component produced from a laminate according to Claim 17, in which a PVC-containing compound is applied to the top layer of the plastic layer of the laminate.

37. Component produced from a laminate according to Claim 29, in which a PVC-containing compound is applied to the top layer of the plastic layer of the laminate.


REMARKS

Claims 1-28 and 30-37 are pending. The claims have been amended to delete the multiple dependent claim status and improve readability.

Claims 30-37 have been added to essentially repeat some of the claims that were previously multiply dependent. The numbering of the new claims starts at 30 because the originally filed application had 29 claims. No new matter is presented by the above amendments. Early and favorable consideration of this application is respectfully requested.

Respectfully submitted,

Date: Sept 7, 2001

By: 
Anthony P. Venturino
Registration No. 31,674

APV/pgw
ATTORNEY DOCKET NO. APV31519

STEVENS, DAVIS, MILLER & MOSHER, L.L.P.
1615 L STREET, N.W., SUITE 850
WASHINGTON, D.C. 20036
TEL. 202-785-0100 / FAX. 202-408-5200

ATTACHMENT I –marked up set of claims

1. (Amended) Process comprising [for] producing a plastic web for coating a metal substrate, in which the plastic [used] is polyester, [characterised in that] wherein the plastic web is produced by extruding a mixture of crystallisable polyester and non-crystallisable polyester.

2. (Amended) Process according to Claim 1, [characterised in that] wherein the polyesters used are copolyesters.

3. (Amended) Process according to Claim 2, [characterised in that] wherein copolyesters based on terephthalic acid are used.

4. (Amended) Process according to Claim 3, [characterised in that] wherein polyesters, which are formed on the basis of PET, are used.

5. (Amended) Process according to [one of Claims 1-4] Claim 1, [characterised in that] wherein the non-crystallisable polyester used is a copolyester containing CHDM (1,4-cyclohexanedimethanol).

6. (Amended) Process according to Claim 5, [characterised in that] wherein the CHDM-modified copolyester is obtained by reacting a mixture of terephthalic acid, ethylene glycol (ethanediol) and CHDM.

7. (Amended) Process according to [one of Claims 1-4] Claim 1, [characterised in that] wherein the non-crystallisable polyester used is a PET/PEN copolymer, which is obtained by reacting a mixture of terephthalic acid, naphthalenedicarboxylic acid and ethylene glycol (ethanediol).

8. (Amended) Process according to [one of Claims 1-7] Claim 1, [characterised in that] wherein the mixture [used] has a non-crystallisable weight fraction, which is greater than 6%.

9. (Amended) Process according to Claim 8, [characterised in that] wherein the mixture [used] has a non-crystallisable weight fraction, which is less than 90%.

10. (Amended) Process according to [Claim 8 or 9] Claim 8, [characterised in that] wherein the mixture used has a non-crystallisable weight fraction which is 25% or greater.

11. (Amended) Process according to [one of Claims 8-10] Claim 8, [characterised in that] wherein the mixture [used] has a non-crystallisable weight fraction which is 33% or greater.

12. (Amended) Process according to [one of Claims 8-11] Claim 8, [characterised in that] wherein the mixture [used] has a non-crystallisable weight fraction which is 50% or greater.

13. (Amended) Process according to [one of Claims 8-12] Claim 8, [characterised in that] wherein the mixture [used] has a non-crystallisable weight fraction which is 66% or greater.

14. (Amended) Process according to [one of Claims 8-13] Claim 8, [characterised in that] wherein the mixture [used] has a non-crystallisable weight fraction which is 75% or greater.

15. (Amended) Laminate comprising a metal substrate and a plastic layer, [characterised in that] wherein the plastic layer comprises an adhesive layer, the adhesive

layer substantially comprising a plastic web produced according to the process described in [one of Claims 1-14] Claim 1.

16. (Amended) Laminate comprising a metal substrate and a plastic layer, [characterised in that] wherein the plastic layer comprises a top layer, the top layer substantially comprising a plastic web produced according to the process described in [one of Claims 1-14] Claim 1.

17. (Amended) Laminate according to [Claims 15 and 16] Claim 15, [characterised in that] wherein there is an intermediate layer between the adhesive layer and the top layer, the intermediate layer substantially comprising a plastic web, which is produced by extruding a polyester.

18. (Amended) Laminate according to Claim 17, [characterised in that] wherein the intermediate layer is produced according to the process described in [one of Claims 1-7] Claim 1.

19. (Amended) Laminate according to Claim 18, [characterised in that] wherein the intermediate layer is produced from a mixture with a non-crystallisable weight fraction which is 10% or greater.

20. (Amended) Laminate according to Claim 19, [characterised in that] wherein the intermediate layer is produced from a mixture with a non-crystallisable fraction which is 33% or greater.

21. (Amended) Screw cap produced from a laminate according to [one of Claims 15-20] Claim 15.

22. (Amended) Crown cork produced from a laminate according to [one of

Claims 15-20] Claim 15.

23. (Amended) Easy open end produced from a laminate according to [one of Claims 15-20] Claim 15.

24. (Amended) Component produced from a laminate according to [one of Claims 16-20] Claim 16, in which a PVC-containing compound is applied to the top layer of the plastic layer of the laminate.

25. Component according to Claim 24, in which the non-crystallisable weight fraction in the top layer is 25% or greater.

26. Component according to Claim 24, in which the weight fraction is 35% or greater.

27. (Amended) Component according to Claim 26, in which the [said] weight fraction is 50% or greater.

28. (Amended) Component according to Claim 27, in which the [said] weight fraction is 66% or greater.

**PROCESS FOR PRODUCING A PLASTIC WEB FOR COATING A METAL
SUBSTRATE, LAMINATE COMPRISING THIS PLASTIC WEB, AND
PRODUCT OR COMPONENT PRODUCED THEREWITH**

5 The invention relates to a process for producing a plastic web for coating a metal substrate, in which the plastic used is polyester. The invention also relates to a laminate containing a plastic web of this nature, and to a product or component which is produced using this laminate.

10 For various reasons, it is often desirable for metal to be provided with an additional layer in the form of a metallic or organic coating. This layer may serve to protect or decorate the metal, depending on its subsequent use. For packaging steel, a combination of a metallic and organic coating layer is generally used, so that the coated material, during its final use, protects the packaged foodstuff well, will not exhibit any corrosion, and the quality of the packaged foodstuff will be maintained.

15 The metallic covering layer used is often tin or chromium with chromium oxide on top, or a combination of these two layers. In the invention described below, good results have been obtained on packaging steel provided with a thin layer of chromium and chromium oxide (ECCS), but use of the invention is not limited to this type of packaging steel.

20 Lacquers are often used as the organic coating layer. Examples are epoxy and epoxyphenol lacquers, polyester lacquers and organosol lacquers, or combinations thereof. Sometimes, using these lacquers involves formability problems, with corrosion occurring or with undesirable substances being released from the lacquer to the packaged foodstuff, or with the undesirable emission of solvents.

25 In this respect, better results are obtained by packaging steel which is provided with a plastic web as a coating layer. Examples of plastics which can be used for this purpose are polypropylene, polyethylene, polyamide and polyester. The plastic web can be applied by producing it in a separate production process, rolling it up and unwinding it again at the location of the coating line, where it is stuck to the metal by the application of heat and pressure. It is also possible to produce a thin, molten web of plastic in the coating line by extrusion, which is applied to the metal in the molten or solidified state.

30 A drawback of using a polyester plastic web, such as a web made from PET (polyethyleneterephthalate), as a coating layer is that it is difficult to adhere this web to the packaging steel sufficiently well for it still to be possible to deform the coated metal without the coating layer becoming detached or ruptured when the coated material is subjected to a (wet) heat treatment.

09/936044-133

Another drawback is that it is difficult to apply an additional layer to the coating layer which then adheres sufficiently firmly to the plastic coating layers which have previously been used. The additional layer is, for example, a PVC-containing sealing compound which is generally used to seal a screw cap on a glass jar in an airtight manner.

Another drawback is that most polyesters crystallize under the influence of heat. A heat treatment is often required in the production process, for example in order to cure a printing or a compound. During this process crystallisation takes place in many polyesters, which in the case of transparent coating layers results in undesirable discoloration, with the colour of the layer becoming opaque and whitish.

One object of the invention is to provide a process for producing a plastic web for coating a metal substrate in which the polyester used adheres securely to the metal even after deformation of the metal together with the coating layer and a (wet) heat treatment.

Another object is to provide a method of this nature in which the polyester provides good adhesion for a PVC-containing compound which is applied to it.

Yet another object is to provide a process of this nature which forms a plastic layer which remains highly transparent during a heat treatment.

Another object of the invention is to use this process to produce laminates, products and components which satisfy one or more of the abovementioned objects.

According to a first aspect of the invention, one or more of these objects are achieved by means of a process of the type described in the preamble in which the plastic web is produced by extruding a mixture of various polyesters.

It has been found that if the constituent components of the polyesters are selected appropriately and an appropriate preparation method is selected, the problems with adhesion to steel after deformation and use, of discoloration of the coating layer caused by a heat treatment, and of adhesion to PVC-containing compounds are solved.

Preferably, the process is such that the polyesters used are copolyesters. With the aid of these copolyesters, it is easy to manipulate the properties of the polyester layer.

Preferably, copolyesters based on terephthalic acid are used. This is a very standard type of copolyester. More preferably, copolyesters which are formed on the basis of PET are used. These are readily available.

According to an advantageous process, the mixture used is a mixture of a crystallisable polyester and a non-crystallisable polyester. By varying the ratio between the crystallisable polyester and the non-crystallisable polyester, it is possible to adapt the properties in such a manner that, for example, a good adhesion to packaging steel or to a PVC-containing compound or a good resistance to a heat treatment is obtained.

Preferably, the process is such that the non-crystallisable polyester used is a copolyester which contains CHDM (1,4-cyclohexanedimethanol). This polyester containing CHDM is very suitable for manipulation of the properties of the polyester layer.

5 Preferably, the CHDM-modified copolyester is obtained by reacting a mixture of terephthalic acid, ethylene glycol (ethanediol) and CHDM.

Alternatively, a process is used in which the non-crystallisable polyester used is a PET/PEN copolymer which is obtained by reacting a mixture of terephthalic acid, naphthalenedicarboxylic acid and ethylene glycol (ethanediol). Other non-crystallizable
10 polyesters may also be suitable in order to obtain the effects described.

Preferably, the mixture used has a non-crystallisable weight fraction which is greater than 6%. If this percentage is lower, the adhesion is in many cases insufficient if the plastic web undergoes a subsequent heat treatment and/or substantial deformation.

Preferably, the mixture used has a non-crystallisable weight fraction which is less
15 than 90%. An excessively high percentage of non-crystallisable polymer in some cases leads to undesirable deformation of the plastic web on a metal substrate, resulting in wrinkles, so that the laminate cannot be used as a substrate for, for example, screw caps which have been printed with heat-curing ink.

Advantageously, the mixture used has a non-crystallisable weight fraction which
20 is approximately 25% or greater. In this way, reasonably good adhesion to PVC-containing compounds is obtained.

Advantageously, the mixture used has a non-crystallisable weight fraction which is approximately 33% or greater. This results in a plastic web which remains highly transparent during a heat treatment; a considerably higher percentage is required for a
25 sterilisation treatment.

Good adhesion to PVC-containing compounds is obtained if the mixture used has a non-crystallisable weight fraction which is approximately 50% or greater, if the plastic-coated metal is at most pasteurised.

For sterilisation applications, it is preferable to use a mixture with a non-
30 crystallisable weight fraction which is approximately 66% or greater.

Very good adhesion to compounds is obtained if the mixture used has a non-crystallisable weight fraction which is approximately 75% or greater.

With regard to the above, it should be borne in mind that it is always desirable for the amount of non-crystallisable polymer in the mixture to be kept as low as possible,
35 since non-crystallisable polymer is much more expensive than crystallisable polymer.

According to a second aspect of the invention, a laminate is provided, comprising a metal substrate and a plastic layer, the plastic layer comprising an adhesive layer, this adhesive layer substantially comprising a plastic web produced according to the process

described above. The laminate thus exhibits good adhesion between the metal substrate and the plastic layer.

Preferably, the laminate is formed in such a manner that the plastic layer comprises a top layer, the top layer substantially comprising a plastic web produced according to the process described above. This gives the top layer good adhesion for a PVC-containing compound.

According to an advantageous embodiment, the plastic layer of the laminate has an adhesive layer and a top layer, an intermediate layer being present between the adhesive layer and the top layer, the intermediate layer substantially comprising a plastic web which is produced by extruding a polyester. Since the top layer and the adhesive layer primarily have an adhesive function and therefore may be thin, an intermediate layer is desirable in order to make the plastic layer sufficiently thick and strong. In order for it to be possible to extrude the plastic layer in a single operation, the intermediate layer also has to be extrudable.

It is possible to produce the intermediate layer using the process described above.

In this case, the intermediate layer is preferably produced from a mixture with a non-crystallisable weight fraction which is approximately 10% or greater. Preferably, this weight fraction is approximately 33% or greater. In this case too, the amount of non-crystallisable polymer must be kept as low as possible, for cost reasons. A higher percentage should be used for a sterilisation treatment.

The laminate can be used to produce, for example, screw caps, crown corks and easy open ends, as well as packagings and components thereof, such as the base, the lid or the body, a deep-drawn and/or wall-ironed can, a base, cap, wall or valve dish of an aerosol can, or a dish or tray, etc.

A third aspect of the invention provides a component produced from a laminate as described above, in which a PVC-containing compound is applied to the top layer of the plastic layer of the laminate.

In this case, the non-crystallisable weight fraction in the top layer is preferably approximately 25% or greater. This makes it possible to achieve good adhesion results between the top layer and the PVC-containing compound.

Preferably, the weight fraction is approximately 35% or greater. This improves the adhesion results.

In order for it to be possible to subject the component to pasteurisation or a similar heat treatment, however, the non-crystallisable weight fraction is preferably 50% or higher in order to be certain to obtain good adhesion.

For sterilisation applications, the said weight fraction is preferably approximately 66% or higher. The adhesion is then good for all PVC-containing compounds which have been investigated.

However, it has been found that the weight fraction of non-crystallisable polyester required in the top layer depends on the compound used, so that the minimum percentage required has to be determined on the basis of the compound employed.

The invention will be explained in more detail below.

5 Experiments have shown that a mixture of, for example, two types of polyester is particularly expedient for producing plastic-coated metal, for example packaging steel. This is, for example, a mixture of crystallisable PET, referred to below as PET A, and non-crystallisable PET, referred to below as PET B. An example of a suitable type of PET for PET A is Eastapak 9921w produced by Eastman Chemical Company. An
10 example of a suitable type of PET for PET B is Eastar PETG 6763, also produced by Eastman Chemical Company.

A number of PET coatings were applied with adhesive, intermediate and top layers in which different quantities of PET B have been mixed with PET A.

Three types of polyester and mixtures thereof were tested. The following text will
15 indicate the characteristics of the various types. The two types of polymer are PET A and PET B as defined above. Mixtures were made from these two types. These two types are copolymers of "normal" PET, in which, during the synthesis, a quantity of ethanediol was replaced with 1,4-cyclohexanedimethanol (referred to throughout the rest of this document as CHDM). PET A has a very low CHDM content, while a
20 PET C, which is to be described below, has a higher CHDM content, and PET B has an even higher CHDM content. PET C is completely copolymerised and has a maximum achievable crystallinity which is lower than that of PET A. Eastar PETG 15086 is used for PET C. A copolymer of this nature has significantly different properties from a mixture of PET A and PET B. These PET grades and mixtures thereof are applied as a
25 coating layer to the substrate.

The product codes of the plastic-coated products used and the associated composition of the plastic are given in the table below (all percentages are by weight).

Code	Adhesive layer	Intermediate layer	Top layer	Steel base
TP628A	PET A			0.21 mm ECCS, T61CA
TP628B	PET C			0.21 mm ECCS, T61CA
P 064	100% PET B	PET A	100% PET B	0.21 mm ECCS, T61CA
P 076	33% PET B	PET A	100% PET B	0.21 mm ECCS, T61CA
P 077	100% PET B	PET A	33% PET B	0.21 mm ECCS, T61CA
P 078	66% PET B	PET A	100% PET B	0.21 mm ECCS, T61CA
P 079	100% PET B	PET A	66% PET B	0.21 mm ECCS, T61CA
P080	100% PET B	PET A	100% PET B	0.21 mm ECCS, T61CA
P 086	100% PET B	PET A	100% PET B	0.155 mm ECCS, DR620CA
P 087	50% PET B	PET A	33% PET B	0.155 mm ECCS, DR620CA
P 088	50% PET B	PET A	50% PET B	0.155 mm ECCS, DR620CA
P 089	50% PET B	33% PET B	50% PET B	0.155 mm ECCS, DR620CA
P 090	75% PET B	PET A	66% PET B	0.155 mm ECCS, DR620CA

The percentage of PET A in the adhesive, intermediate and top layers is 100 minus the PET B percentage indicated. In variants TP628A and TP628B, a single-layer coating was applied.

Variants P076 – P080 and P086 – P090 were used for adhesion tests.

5 The reference material used in the compound tests was a lacquered can.

Specifications:

- steel base: 0.24 mm T57CA
- tin plating: 2.8/2.8 g/m²
- passivation: 311 (approx. 5 mg/m² Cr)
- 10 • lacquer system (adhesive lacquer: approx. 5 g/m² and top lacquer: approx. 12 g/m², as is customarily used for screw caps).

To test the compound adhesion directly after application, a layer of compound is applied to the coating variant to be examined, and this layer is cured in a hot air furnace under suitable conditions. The specimen is cut into narrow strips, after which a blade is used to cut off a small piece of the compound applied. A 180° peel test was then carried out in a tensile strength tester, using the exposed substrate and the cut-out piece of compound as the point of engagement. The adhesion of the compound is excellent if the compound layer breaks during the peel test and sufficient if the peel strength is greater than 1 N/mm.

15 To establish the compound adhesion after sterilisation, after the compound has been applied and cured the entire specimen is placed in a high-pressure pan containing demineralised water. The pan is heated to a temperature of 121°C, after which the specimen is sterilised for 1 hour at this temperature. After cooling, the specimen is again cut into narrow strips and is kept moist through being immersed in demineralised water until, shortly afterwards, a peel test is carried out following the procedure described above.

20 In the first instance, it was attempted to carry out this test as an adhesion test for the compound. It was found that the adhesion of the compound to the PET was stronger than the adhesion of PET to ECCS. This method was therefore found to be suitable for determining the adhesion to ECCS.

25 In order to determine the adhesion after sterilisation, use is made of the (particular) phenomenon that it is possible to obtain excellent adhesion between cured PVC-containing compound and a top layer comprising 100% PET B. The procedure is as follows.

35 Slightly wider strips of P064 are laid onto the strips of material with cured compound already on them. This *sandwich* is placed between two stainless steel plates which are fixed at the four corners by means of a nut and bolt (manually tightened). This assembly is placed in a high-pressure pan containing demineralised water and is

heated. After 121°C (1 bar excess pressure) has been reached, sterilisation is carried out for a further hour. After cooling, the specimens which have been placed on top of one another are removed from the container and placed in a glass beaker containing water, in order to keep the specimens moist (drying generally allows the adhesion to improve).

- 5 To carry out the peel test, an incision is then again made between the compound and the coated material to be tested. Then, the ends of the specimen plate to be tested and the support plate made of P064 are clamped in the test stand. Then, a 180° peel test is carried out in the same way as that described above.

10 The adhesion determined using this method represents a measure of adhesion in the wet state and thus provides an indication of the adhesion to, for example, the inside of a sterilised packaging.

There is a considerable difference in adhesion which can be achieved between compound and coating layer amongst the tested mixtures of the PET A and PET B variants, and PET C (copolymer).

- 15 PET A (TP628A) and PET C (TP628B) exhibit scarcely any adhesion to a PVC-containing compound. In both cases, the adhesion is very inadequate in the dry state. These variants are not suitable for use as a coating for the inside of screw caps (forces measured from approx. 0.1-0.2 N/mm; the peel strength should be above 1 N/mm).

20 In principle, very good adhesion can be obtained between PVC-containing compound and a top layer comprising a mixture of PET A and PET B. A number of PVC-containing compounds were tested. Some of the compounds are (according to the supplier) particularly suitable for pasteurisation, other types for sterilisation applications. Compounds from various suppliers were tested. As can be seen from the table containing the test results concerning the compound adhesion directly after
25 application, the percentage of PET B which is required depends on the compound tested.

Adhesion of a number of compounds to the tested variants immediately after application

30

Variant code	Compound 1	Compound 2	Compound 3	Compound 4
P064	Breakage	Breakage	Not tested	Not tested
P077	Moderate adhesion	Breakage	Not tested	Not tested
P079	Breakage	Breakage	Not tested	Not tested
P086	Not tested	Not tested	Breakage	Breakage

P087	Breakage	Breakage	No adhesion	No adhesion
P088	Breakage	Breakage	Breakage	Strong adhesion
P089	Breakage	Breakage	Breakage	Breakage
P090	Breakage	Breakage	Breakage	Breakage

Compound 1: Compound from supplier A suitable for pasteurisation (fat-containing foodstuffs)

Compound 2: Compound from supplier A for sterilisation applications (fat-containing foodstuffs)

Compound 3: Compound from supplier B suitable for hot fill and pasteurisation applications

Compound 4: Compound from supplier B suitable for sterilisation applications

5

The compound adhesion is optimum if breakage occurs during the peel test. If good adhesion is obtained immediately after application (breakage in the compound during the peel test), in all cases it was found that, after sterilisation or pasteurisation, the adhesion of the compounds to the PET coating layer was greater than that of the coating layer to the ECCS. Good compound adhesion even after pasteurisation or sterilisation is essential for successful use of these materials, since a treatment of this nature is almost always used.

In all cases, it was found that the compounds tested exhibited highly insufficient adhesion to TP628A and TP628B. Of these variants, variant TP628B (PET C) exhibits slightly less poor adhesion, but still adheres insufficiently to PVC-containing compound.

For non-processable/pasteurisation applications, $\geq 50\%$ PET B in the top layer is sufficient to obtain good adhesion to all the compounds tested. For sterilisation applications, a higher percentage is required: $\geq 66\%$ PET B in the top layer. At these concentrations of PET B, all the compounds tested are suitable. However, for both cases it is possible that lower percentages may also give good results, depending on the compound used. Therefore, by making use of specific compounds for specific applications, it is possible to use lower percentages of PET B in the top layer.

By sealing the specimen to a reference specimen with a compound applied thereon, it is possible to determine the force which is required to pull the compound off. If the adhesion of the compound to the PET is sufficiently great, it is not the adhesion of the compound to the plastic, but rather the adhesion of the plastic layer to the steel which is measured. This is lower under wet conditions than the adhesion under dry conditions. A number of results are given in the table.

Variant code	F _{mean} Compound 1 N/mm	F _{mean} Compound 2 N/mm	Adhesive layer
P064	2.5; 2.6	1.7; 1.7	PET B
P076	1.2; 3.0	0.1*; 0.3*	33% PET B
P077	2.4; 2.4	1.6; 1.6	PET B
P078	2.8; 3.1	0.4*; 2.1, 0.6*, 0.7*	66% PET B
P079	2.6; 2.8	1.7; 1.7	PET B
P080	2.3; 2.5	0.9; 1.2	PET B
P088	n.d.	0.5*, 0.3*	50% PET B
P089	n.d.	0.3*, 0.2*	50% PET B
P090	n.d.	0.6, 1.0	75% PET B
Lac. Ref	2.2; 2.3	2.6; 1.4, 1.8, 1.3	
* : no adhesion or scarcely any adhesion, n.d.: not determined			

The impression of the coating with a 100% PET B adhesive layer is relatively consistent, although the two types of compound give a different effect to the adhesion. In the variants with an adhesive layer containing 33% PET B, there is a somewhat greater spread. It is clear that the adhesion to steel when using compound 2 is considerably lower (insufficient). This effect is also found when using compound 1, although in this case the effect is less intensive. With compound 1, the adhesion appears to remain sufficient in all cases.

The relationship between the quantity of PET B in the adhesive layer and the adhesion to the ECCS (under wet conditions) measured with compound 2 can be described according to the following formula:

$$\text{Peel strength} = 1.4 \cdot 10^{-4} * P^2$$

where P is the percentage of PET B in the adhesive layer and the peel strength is expressed in N/mm.

In the case of compound 1, the measured values are much higher. The difference between the two types is that compound 2 is a sterilisation compound, while compound 1 is more suitable for hot fill and pasteurisation. In this case, the relationship can be described by the following equation

$$\text{Peel strength} = \ln P - 1.96$$

A clear conclusion which can be drawn from these measurements is that different compounds lead to different adhesion. For certain applications, low PET B contents are possible.

5 The top layer of a PET coating (intended in particular for screw caps) must exhibit good adhesion to a PVC-containing compound. Adhesion of PET to a PVC is difficult to achieve. It is generally accepted that PET does not adhere to PVC. Known solutions for improving the adhesion to compound are relatively complex and, in some cases, use PVC-containing layers. With the above-described method of mixing a
10 crystallisable PET and a non-crystallisable PET provides very good adhesion in a simple manner.

For the intermediate layer, it is important, in the case of transparent coating layers, that the appearance of the layer should not change visibly as a result of (dry) heat treatments. It has been found that with the crystallisable polyesters normally used,
15 such as PET A, undesirable discoloration takes place as a result of a heat treatment. It has been found that if a polyester layer comprising a mixture of mainly crystallisable polyester (PET A) and some non-crystallisable polyester (PET B) is used, it is not possible to detect any change in appearance when used as transparent coating layer for metals which still have to undergo a heat treatment (for example for curing a compound
20 or printing).

It has been found that in the case of sterilisation and pasteurisation, the adhesion of a PET A or PET C is insufficient to obtain a suitable material for use as base material for metal packaging.

The adhesion of PET to steel is considerably improved by using a mixture of
25 PET B and PET A. An excessively high percentage of PET B leads to undesirable deformation of the coating (wrinkling), with the result that the laminate cannot be used as a material for, in particular, screw caps printed with heat-curing ink.

A comparison between PET C and a mixture of PET B and PET A indicates the importance of choosing a mixture. For example, compound adhesion to PET C is
30 absolutely insufficient.

This means that other polyesters which have a non-crystallisable character will also give a similar effect, for example copolymerised PET in which approx. 15% of the terephthalic acid weight fraction is replaced by naphthalenedicarboxylic acid, preferably naphthalene-2,6-dicarboxylic acid. The pure polyester of
35 naphthalenedicarboxylic acid and ethylene glycol (PEN) has the additional advantage of very good barrier properties.

It will be understood that the above mentioned examples do not limit the invention in any way. The scope of protection is defined by the claims which follow.

CLAIMS

1. Process for producing a plastic web for coating a metal substrate, in which the plastic used is polyester, characterised in that the plastic web is produced by extruding a mixture of various polyesters.
2. Process according to Claim 1, characterised in that the polyesters used are copolyesters.
3. Process according to Claim 2, characterised in that copolyesters based on terephthalic acid are used.
4. Process according to Claim 3, characterised in that polyesters which are formed on the basis of PET are used.
5. Process according to one of the preceding claims, characterised in that the mixture used is a mixture of a crystallisable polyester and a non-crystallisable polyester.
6. Process according to Claim 5, characterised in that the non-crystallisable polyester used is a copolyester containing CHDM (1,4-cyclohexanedimethanol).
7. Process according to Claim 6, characterised in that the CHDM-modified copolyester is obtained by reacting a mixture of terephthalic acid, ethylene glycol (ethanediol) and CHDM.
8. Process according to Claim 5, characterised in that the non-crystallisable polyester used is a PET/PEN copolymer which is obtained by reacting a mixture of terephthalic acid, naphthalenedicarboxylic acid and ethylene glycol (ethanediol).
9. Process according to one of Claims 5-8, characterised in that the mixture used has a non-crystallisable weight fraction which is greater than 6%.
10. Process according to Claim 9, characterised in that the mixture used has a non-crystallisable weight fraction which is less than 90%.

11. Process according to Claim 9 or 10, characterised in that the mixture used has a non-crystallisable weight fraction which is approximately 25% or greater.
- 5 12. Process according to one of Claims 9-11, characterised in that the mixture used has a non-crystallisable weight fraction which is approximately 33% or greater.
13. Process according to one of Claims 9-12, characterised in that the mixture used has a non-crystallisable weight fraction which is approximately 50% or greater.
- 10 14. Process according to one of Claims 9-13, characterised in that the mixture used has a non-crystallisable weight fraction which is approximately 66% or greater.
- 15 15. Process according to one of Claims 9-14, characterised in that the mixture used has a non-crystallisable weight fraction which is approximately 75% or greater.
- 16 16. Laminate comprising a metal substrate and a plastic layer, characterised in that the plastic layer comprises an adhesive layer, the adhesive layer substantially comprising a plastic web produced according to the process described in one of Claims 1-15.
- 20 17. Laminate comprising a metal substrate and a plastic layer, characterised in that the plastic layer comprises a top layer, the top layer substantially comprising a plastic web produced according to the process described in one of Claims 1-15.
- 25 18. Laminate according to Claims 16 and 17, characterised in that there is an intermediate layer between the adhesive layer and the top layer, the intermediate layer substantially comprising a plastic web which is produced by extruding a polyester.
- 30 19. Laminate according to Claim 18, characterised in that the intermediate layer is produced according to the process described in one of Claims 1-8.
- 35 20. Laminate according to Claim 19, characterised in that the intermediate layer is produced from a mixture with a non-crystallisable weight fraction which is approximately 10% or greater.

21. Laminate according to Claim 20, characterised in that the intermediate layer is produced from a mixture with a non-crystallisable fraction which is approximately 33% or greater.
- 5 22. Screw cap produced from a laminate according to one of Claims 16-21.
23. Crown cork produced from a laminate according to one of Claims 16-21.
24. Easy open end produced from a laminate according to one of Claims 16-21.
- 10 25. Component produced from a laminate according to one of Claims 17-21, in which a PVC-containing compound is applied to the top layer of the plastic layer of the laminate.
- 15 26. Component according to Claim 25, in which the non-crystallisable weight fraction in the top layer is approximately 25% or greater.
27. Component according to Claim 25, in which the weight fraction is approximately 35% or greater.
- 20 28. Component according to Claim 27, in which the said weight fraction is approximately 50% or greater.
- 25 29. Component according to Claim 28, in which the said weight fraction is approximately 66% or greater.

COMBINED DECLARATION AND POWER OF ATTORNEY FOR
UTILITY PATENT APPLICATION (Includes PCT)

Attorney Docket No.
APV31519

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name; that

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural inventors are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

PROCESS FOR PRODUCING A PLASTIC WEB FOR COATING A METAL SUBSTRATE, LAMINATE COMPRISING THIS PLASTIC WEB, AND PRODUCT OR COMPONENT PRODUCED THEREWITH

the specification of which (check one)

☐ is attached hereto.

☐ was filed on _____ as Application Serial No. _____ and was amended on _____ (if applicable)

☒ was filed as PCT International Application No. PCT/EP00/02211 on March 9, 2000, and was filed in the U.S. National Stage on September 7, 2001 as U.S. Patent Application No. 09/936,044.

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to the examination of this application in accordance with Title 37, Code of Federal Regulations, §1.56(a).

I do not know and do not believe the claimed invention was ever known or used in the United States of America before my or our invention thereof, or patented or described in any printed publication in any country before my or our invention thereof or more than one year prior to this application, that the same was not in public use or on sale in the United States of America more than one year prior to this application, that the invention has not been patented or made the subject of an inventor's certificate issued before the date of this application in any country foreign to the United States of America on an application filed by me or my legal representatives or assigns more than twelve months prior to this application.

I hereby claim foreign priority benefits under Title 35, United States Code §119 and/or §365(a)(b) of any foreign application(s) and United States provisional applications for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application(s) on which priority is claimed:

Prior Foreign and U.S. Provisional Application(s)

Priority Claimed

<u>1011518</u>	<u>NL</u>	<u>10 March 1999</u>	<input checked="" type="checkbox"/>	<input type="checkbox"/>
(Number)	(Country)	Day/Month/Year Filed	Yes	No
<u>1013101</u>	<u>NL</u>	<u>21 September 1999</u>	<input checked="" type="checkbox"/>	<input type="checkbox"/>
(Number)	(Country)	Day/Month/Year Filed	Yes	No

I hereby claim the benefit under Title 35, United States Code, §120 and/or 5365(c) of any United States application(s) or PCT international application(s) designating the United States of America listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior application(s) in the manner provided by the first paragraph of Title 35, United States Code, §112, I acknowledge the duty to disclose material information as defined in Title 37, Code of Federal Regulations, §1.56(a) which occurred between the filing date of the prior application and the national or PCT international filing date of this application:


Application Serial No.	Filing Date	Status
		(patented, pending, abandoned)

Application Serial No.	Filing Date	Status
		(patented, pending, abandoned)

I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith; Stevens, Davis, Miller & Mosher, L.L.P.; Anthony P. Venturino, Reg. No. 31,674; James E. Ledbetter, Reg. No. 28,732; and Thomas P. Pavalko, Reg. No. 31,689. Direct all telephone calls to telephone no. 202-785-0100 and faxes to 202-408-5200.

Address all correspondence to 1615 L Street, N.W., Suite 850, Washington, D.C. 20036.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true, and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Full Name of Sole, First Inventor	Inventor's Signature	Date
Petrus Cornelis Jozef BEENTJES		7-12-2001
Residence:		Citizenship
NL-1902 AA Castricum		Dutch
Post Office Address:		
Cieweg 43		
NL-1902 AA Castricum, The Netherlands	114X	

Full Name of Second, Joint Inventor	Inventor's Signature	Date
Adrianus Johannes DEN HARTOG		7/12/01
Residence:		Citizenship
NL-2315 EB Leiden, The Netherlands NLX		Dutch
Post Office Address: Kooilaan 17 NL-2315 EB Leiden, The Netherlands		
Full Name of Third, Joint Inventor	Inventor's Signature	Date
Willem Jan VAN VEENEN		11-12-2001
Residence:		Citizenship
NL-1019 HJ Amsterdam The Netherlands NLX		Dutch
Post Office Address: Zeeburgerkade 164 1019 HJ Amsterdam NL-1019 HJ Amsterdam, The Netherlands		